

WNMP 060408 NN LT 10 & LT 1000

Material Group	Gr. N°	VDI Group	Material Examples*	Hardness	D.O.C. [mm]		Feed [mm/rev]		Amax [mm ²]	V _c [m/min]		Optimal cutting conditions		
					min	max	min	max		min	max	D.O.C.	Feed	V _c
Steel	Non-alloyed	1	1 C35, Ck45, 1020, 2 1045, 1060, 3 28Mn6	125 HB 190 HB 250 HB	0.5	2.5	0.21	0.50 0.50 0.45	1.17 1.17 0.98	180	280 250	2.2	0.35	240 220 200
		2	6 42CrMo4, St50, 4,6 Ck60, 4140, 4340, 5,7 100Cr6	180 HB 230 HB 280 HB 350 HB	0.5	2.5 2.0 2.0 1.8	0.21 0.21 0.18 0.18	0.45 0.45 0.40 0.40	0.78 0.78 0.78 0.65	120	280 250 210 180	2.2 1.8 1.8 1.6	0.32 0.32 0.30 0.30	200 180 150 130
		3	10 X40CrMoV5, 10 H13, M42, D3, 11 S6-5-2, 12Ni19	220 HB 280 HB 320 HB 350 HB	0.5	2.0 2.0 1.5 1.5	0.18 0.18 0.18 0.18	0.40 0.40 0.35 0.35	0.78 0.78 0.52 0.52	70	190 150 130 110	1.8 1.8 1.5 1.5	0.30 0.30 0.28 0.28	140 120 100 90
	Stainless Steel	4	14 304, 316, 14 X5CrNi18-9	180 HB 240 HB	0.5	2.5 2.5	0.20 0.20	0.40 0.40	0.78 0.65	170 160	270 220	2.2	0.35 0.32	190 170
		5	14 X2CrNiN23-4, 14 S31500	290 HB 310 HB	0.5	2.0 2.0	0.18 0.18	0.35 0.35	0.52 0.52	80 70	150 140	1.8	0.28	100 90
		6	12 410, X6Cr17, 13 17-4 PH, 430	200 HB 42 HRC	0.5	2.5 2.0	0.22 0.22	0.40 0.40	0.65 0.65	170 120	250 190	2.2 2.0	0.32	190 130
	Cast Iron	7	15 GG20, GG40, 15 EN-GJL-250, 16 No30B	150 HB 200 HB 250 HB	0.5	2.5 2.5 2.5	0.15 0.15 0.15	0.60 0.60 0.55	1.30 1.17 1.17	170 160 150	250 230 210	2.2	0.35	200 180 160
		8	17,19 GGG40, GGG70, 17,19 50005 18,20	150 HB 200 HB 250 HB	0.5	2.5 2.5 2.5	0.15 0.15 0.15	0.50 0.50 0.50	0.98 0.85 0.78	120	250 230 190	2.2	0.30	180 160 140
		9	31,32 Incoloy 800 33 Inconel 700 34 Stellite 21	240 HB 250 HB 350 HB	0.5	1.5 1.5 1.5	0.20 0.20 0.20	0.35 0.35 0.35	0.46 0.46 0.46	25 25 23	45 45 40	1.5	0.28	32 30 28
	High Temp. Alloys	10	36 TiAl6V4 37 T40	- -	0.5	2.0 1.5	0.20 0.20	0.40 0.35	0.52 0.46	45 35	65 55	1.5	0.33 0.30	55 45
		11	38 X100CrMo13, 38 440C, 38 G-X260NiCr42	45 HRC 50 HRC 55 HRC	0.5	1.6 1.3 1.3	0.11 0.11 0.11	0.30 0.25 0.20	0.39 0.26 0.20	50 40 40	100 90 80	1.5 1.0 1.0	0.25 0.20 0.18	80 70 60
Hardened Mat.	Chilled Cast Iron		40 Ni-Hard 2	400 HB	0.5	1.3	0.11	0.25	0.26	40	60	1.0	0.18	50
	White Cast Iron		41 G-X300CrMo15	55 HRC	0.5	1.3	0.11	0.20	0.20	30	50	1.0	0.15	40
NF	Al (>8%Si)	12	25 AISI12	130 HB	0.5	3.0	0.20	0.60	1.80	200	400	2.2	0.40	280