

WNMP 080408 NN LT 10 & LT 1000

Material Group	Gr. N°	VDI Group	Material Examples*	Hardness	D.O.C. [mm]		Feed [mm/rev]		Amax [mm²]	V _c [m/min]		Optimal cutting conditions		
					min	max	min	max		min	max	D.O.C.	Feed	V _c
Steel	Non-alloyed	1	1 C35, Ck45, 1020,	125 HB	0.5	3.5	0.21	0.50	1.80	180	330	2.4	0.35	240
			2 1045, 1060,	190 HB		3.5		0.50	1.80		280			220
			3 28Mn6	250 HB		3.5		0.45	1.50		250			200
	Low alloyed	2	6 42CrMo4, St50,	180 HB	0.5	3.5	0.21	0.45	1.20	120	280	2.4	0.32	200
			4,6 Ck60, 4140, 4340,	230 HB		2.8		0.45	1.20		250			180
			5,7 100Cr6	280 HB		2.8		0.40	1.20		210			150
			8	350 HB		2.5		0.40	1.00		180			130
	High alloyed	3	10 X40CrMoV5,	220 HB	0.5	2.8	0.18	0.40	1.20	70	190	2.0	0.30	140
			10 H13, M42, D3,	280 HB		2.8		0.40	1.20		150			120
			11 S6-5-2, 12Ni19	320 HB		2.1		0.35	0.80		130			100
				350 HB		2.1		0.35	0.80		110			90
Stainless Steel	Austenitic	4	14 304, 316,	180 HB	0.5	3.5	0.20	0.40	1.20	170	270	2.4	0.25	190
			14 X5CrNi18-9	240 HB		3.5		0.40	1.00		160			170
	Duplex	5	14 X2CrNiN23-4,	290 HB	0.5	2.8	0.18	0.35	0.80	80	150	2.0	0.28	100
			14 S31500	310 HB		2.8		0.35	0.80		70			90
	Ferritic & Martensitic	6	12 410, X6Cr17,	200 HB	0.5	3.5	0.22	0.40	1.00	170	250	2.4	0.32	190
			13 17-4 PH, 430	42 HRc		2.8		0.40	1.00		120			130
Cast Iron	Grey	7	15 GG20, GG40,	150 HB	0.5	3.5	0.15	0.60	2.00	170	250	2.4	0.35	200
			16 EN-GJL-250,	200 HB		3.5		0.60	1.80		160			180
			16 No30B	250 HB		3.5		0.55	1.80		150			160
	Malleable & Nodular	8	17,19 GGG40, GGG70,	150 HB	0.5	3.5	0.15	0.50	1.50	120	250	2.4	0.30	180
			17,19 50005	200 HB		3.5		0.50	1.30		230			160
			18,20	250 HB		3.5		0.50	1.20		190			140
High Temp Alloys	Fe, Ni & Co based	9	31,32 Incoloy 800	240 HB	0.5	2.1	0.20	0.35	0.70	25	45	1.6	0.28	32
			33 Inconel 700	250 HB		2.1		0.35	0.70		25			30
			34 Stellite 21	350 HB		2.1		0.35	0.70		23			28
	Ti based	10	36 TiAl6V4	-	0.5	2.8	0.20	0.40	0.80	45	65	1.6	0.33	55
			37 T40	-		2.1		0.35	0.70		35			45
Hardened Mat.	Steel	11	38 X100CrMo13,	45 HRc	0.5	1.8	0.11	0.30	0.60	50	100	1.6	0.25	80
			38 440C,	50 HRc		1.5		0.25	0.40		40			70
			38 G-X260NiCr42	55 HRc		1.5		0.20	0.30		40			60
	Chilled Cast Iron		40 Ni-Hard 2	400 HB	0.5	1.5	0.11	0.25	0.40	40	60	1.2	0.18	50
	White Cast Iron		41 G-X300CrMo15	55 HRc	0.5	1.5	0.11	0.20	0.30	30	50	0.8	0.15	40
NF	Al (>8%Si)	12	25 AlSi12	130 HB	0.5	4.2	0.20	0.60	1.80	200	400	2.4	0.40	280